

# ACRYDEAL<sup>®</sup> - S

PAINTABLE, MILDEW RESISTANT, PROFESSIONAL GRADE  
SILICONIZED ACRYLIC SEALANT.

DEAL International Inc. • P.O. Box 10088 • Rochester, NY 14610 • 585-288-4444 • Fax: 585-288-4578

## PRODUCT DESCRIPTION

ACRYDEAL<sup>®</sup>-S is a one part, fast curing, odorless sealant based on acrylic emulsion, that remains flexible after cure. It adheres very well to most non-porous and porous substrates. It is paintable once cured. Painting over the sealant creates invisible joints which is desirable in the interior of a house.

## USES

- **Windows & Door Install** - Interior recommended.
- **HVAC** - Joints in ventilation & air-conditioning ductworks.
- **Plumbing** - Bathtubs, Enclosures.
- **Kitchen & Bath counter top & cabinets.**
- Minor wall damage repair before painting.
- Tile installation.
- Any application that requires painting after cure.
- Good adhesion to: PVC, vinyl, concrete, brick, aluminum, wood, marble, granite, tile, ceramics, iron, coated metals (Coil for capping), melamine and lots more...

## BENEFITS

- **PAINTABLE!** - Paint-able after cure.
- **NO SMELL!** - Better homeowner experience.
- **NO DRIPPING!** - No messy carpets, jeans or sills.
- **NO POPPING!** - Perfect bead and not messy walls.
- **FAST SKING & CURE TIME** - Will not allow your work to be damaged once you leave.
- **NO SHRINKAGE** - What you apply is what you get!
- **NO BLACKING OVER TIME** - Mildew / Fungus resistant. Just wipe with wet cloth to clean.
- **GET PERFECT BEAD** - Thick paste, no air pockets and removable nozzle assure consistent bead.
- **YOUR INSTALLERS WILL LOVE YOU FOR GETTING ACRYDEAL<sup>®</sup>-S**

## TECHNICAL CHARACTERISTICS

|                            |  |
|----------------------------|--|
| Shore A Hardness           | 24   |
| Movement Capability        | +/- 12%  |
| Tooling Time               | 10-20 min (77°F @ 50% RH)  |
| Cure Time                  | 24 hours (77°F @ 50% RH)   |
| Full cure                  | 2-4 days (77°F @ 50% RH)   |
| Specific Gravity           | 1.6  |
| Application Temp.          | 40° F to 95° F   |
| Service Temperature        | -5° F to +180° F   |
| Elongation at break        | 300%   |
| Life expectancy            | 15+ years  |
| Corrosion-nonferrous metal | None   |
| SPECIFICATIONS             | C731, C732, C733, C734<br>C736, D2202, D2203,<br>D2377, ASTM C839-76 |

## PACKAGING & STORAGE

ACRYDEAL<sup>®</sup>-S is supplied in 300 ml (10.1 fl. oz) cartridges with removable nozzles, 24 cartridges per case & 56 cases per skid (1,344 cartridges/pallet).

It has a shelf life of 12 months stored in a dry place at or below +25°C in its original container.

## DIRECTION FOR USE

- Surfaces should be clean and dry, free of dust or grease.
- Apply sealant firmly into joint or corner to provide a solid fill.
- Tool down using spatula or stick dipped in soapy water.
- Wait 24 hours before exposure to water.
- Do not use in area confined from atmospheric moisture, that may bleed oils or solvents.
- Paint only after sealant is cured.



## FOR ORDERING:

DEAL International Inc. • P.O. Box 10088; Rochester, NY 14610 • WWW.DIIHQ.COM  
Tel: (585) 288-4444 • Order Fax: (585) 444-1456 • Email: orders@diisoft.com

**NOTICE TO PURCHASER:** DEAL International Inc. warrants its products to conform to their published specifications. The user shall determine the suitability of the product to their particular application. THE FOREGOING WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED, INCLUDING THOSE OF THE MERCHANTABILITY OR FITNESS FOR ANY PURPOSE NOT EXPRESSLY SET FORTH HEREIN. Manufacturer's and seller's liability for damage hereunder shall not exceed the purchase value of the goods used. IN NO EVENT SHALL MANUFACTURER OR SELLER BE RESPONSIBLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES ARISING OUT OF OR IN CONNECTION WITH THE USE OF THIS PRODUCT BY BUYER, BUYER'S USER, OR ANY OTHER PERSON. Notification of claim must be sent in writing to DEAL International Inc.